



Castrol Alpha SP Range

Gear oils

Description

The Castrol Alpha™ SP gear oil range of high quality lubricants are based upon highly refined mineral oil, enhanced with an advanced extreme pressure additive technology providing outstanding thermal stability and high load carrying capacity.

The advanced extreme pressure additive system not only provides high load carrying capacity, but was designed to provide microscopic wear protection. Microscopic wear protection, also known as micropitting protection, is critical in preventing destructive wear at the micro level therefore extending gear life and meeting the evolving demands of smaller and higher output gear boxes.

Application

- The Alpha SP range is recommended for the lubrication of industrial gear boxes using forced circulation or splash and oil bath lubrication.
- They may be used for the lubrication of spur and helical gears and in some lightly loaded worm type gear applications.
- They have very good viscosity characteristics to ensure that starting torques are not excessively high in cold operating conditions.
- The additives are compatible with the ferrous and non-ferrous metals used in industrial gear units.
- The Alpha SP range is fully compatible with nitrile, silicone and fluropolymer seal materials.

Alpha SP is classified as follows: DIN Classification is CLP.

The Alpha SP range meets the requirements of:

- DIN 51517 Part 3
- AGMA 9005 - D94
- US Steel 224
- David Brown Type E
- Hansen Transmissions
- Flender
- Suitable for Müller Weingarten equipment

Advantages

- 'Clean gear' additive technology ensures low deposit formation and enhanced filter life.
- Full Extreme Pressure (EP) performance* gives maximum protection of gears against wear and shock-loading.
- Good water separation and demulsification characteristics means reduced down time through prolonged lubricant life and increased equipment reliability.
- High protection against corrosion and wear resulting in less maintenance.

*ISO 220 grade achieved FZG >14 rating under a16.6./90(double speed) test conditions.

Typical Characteristics

Name	Method	Units	SP 46	SP 68	SP 100	SP 150	SP 220	SP 320	SP 460	SP 680	SP 1000
AGMA No.	-	-	-	2EP	3EP	4EP	5EP	6EP	7EP	8EP	-
ISO Viscosity Grade	-	-	46	68	100	150	220	320	460	680	1000
Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m ³	880	880	890	890	890	900	900	920	930
Kinematic Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm ² /s	46	68	100	150	220	320	460	680	1000
Kinematic Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm ² /s	6.8	8.8	11.2	14.5	18.7	24.0	30.5	37.3	43.6
Viscosity Index	ISO 2909 / ASTM D2270	-	>95	>95	>95	>95	>95	>95	>95	89	80
Pour Point	ISO 3016 / ASTM D97	°C/°F	-21/-6	-21/-6	-21/-6	-18/0	-15/5	-9/16	-9/16	-6/21	-3/27
Flash Point - open cup method	ISO 2592 / ASTM D92	°C/°F	215/420	215/420	219/427	223/435	225/438	226/440	225/438	229/445	229/445
Foam Sequence I - tendency / stability	ISO 6247 / ASTM D892	ml/ml	10/0	10/0	10/0	10/0	10/0	10/0	10/0	10/0	10/0
Copper corrosion (3 hrs @ 100°C/212°F)	ISO 2160 / ASTM D130	Rating	1b	1b	1b	1b	1b	1b	1b	1b	1b
Rust test - synthetic seawater (24 hrs)	ISO 7120 / ASTM D665B	Rating	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Timken OK Load test	ASTM D2782	kg/lb	-	39/85	43/95						
FZG Gear Scuffing test - A/8.3/90	ISO 14635-1	Failure Load Stage	-	>12							
FZG Micropitting test @ 90°C/194°F	FVA 54-7	Failure Load Stage / Micropitting Rating	-	-	-	>10/High					

Subject to usual manufacturing tolerances.

Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings. Products should not be stored above 60°C, exposed to hot sun or freezing condition.

Castrol Alpha SP Range

13 Apr 2016

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

10 Junction Avenue, Parktown, Johannesburg, 2193, South Africa

+27 11 488 5111, 0860 222 166 (SA), 0800 111 551 (SA)

www.castrol.co.za