

Optigear™ 1100 Range

Gear oils with TGOA

Description

Castrol Optigear™ 1100 Range (previously called Tribol™ 1100 Range) of high-performance extreme pressure gear oils, developed to tackle wear-related problems in heavily loaded industrial gears and bearings. Developed for service in enclosed gear drives, sliding and rolling bearings, the Optigear 1100 gear oils are typically used where heavy and shock load conditions prevail.

Optigear 1100 is formulated with Tribol Gear Oil Additive (TGOA) Plastic Deformation (PD) additive. TGOA PD helps improve performance when operating temperature and loads reach a certain level of activation energy, by enabling the microsmoothing of surface roughness without increasing wear. The smoothed surface delivers optimum wear protection and an extremely low coefficient of friction, especially in applications which experience extreme pressure, shock loads, vibrations or low speeds. TGOA PD helps to protect against scuffing and shock loading, while maintaining a high load carrying capacity, and can help prevent the progression of micro-pitting in pre-damaged gears.

Specific grades within the Optigear 1100 range meet the requirements of DIN 51517 part 3 CLP and the requirements of a wide range of industrial bodies and equipment manufacturers.

Application

Optigear 1100 oils are particularly valuable in the running-in phase as well as in applications where surfaces have already been damaged in the micro-range.

Typical applications are spur, helical, herringbone, bevel and planetary gears as well as in geared couplings.

Optigear 1100 gear oils may be used in rolling and sliding bearings.

Particularly suitable for Heavy duty reciprocating pumps for drilling mud or cement placement offshore and onshore drilling sites. Optigear 1100 oils have good water separation properties.

Advantages

Compared to conventional non-PD oils, Castrol Optigear 1100 can deliver the following advantages:

- Tests have shown a reduction in the coefficient of friction of up to 60% over conventional oils without PD technology¹ which can deliver energy savings, lower lubricant and component temperatures and improve operational efficiency
- In laboratory tests Castrol PD additives were shown to prevent the progression of micro-pitting in pre-damaged gears. Non-PD oils used in pre-damaged gears showed existing wear levels increased up to three times²
- Smoothing existing gear damage reduces the cost of repairs and replacements and improves operating efficiency by increasing equipment reliability
- Friction, heat and vibration are reduced
- Oil with Castrol PD additives provides superior protection with wear levels of less than half those observed in tests with conventional non-PD oil³ to help extend planned gear and bearing life
- Extended lubricant service life and relubrication intervals can help to reduce costs and waste oil disposal
- Full load operation is achieved in a short time, virtually eliminating the running-in period

¹In-house testing on SRV test rig; steel ball against steel plate.

²In-house modified FZG micro-pitting test.

³Independent MPR testing carried out by Powertrib showed weight loss was less than half that recorded through use of a conventional non-PD oil.

Typical Characteristics

Name	Method	Units	1100 / 150	1100 / 220	1100 / 320	1100 / 460	1100 / 680	1100 / 1000	1100 / 1500
ISO Viscosity Grade	ISO 3448	-	150	220	320	460	680	1000	1500
Density @ 15°C	ASTM D4052/ ISO 12185	kg/m ³	901	902	912	920	930	932	935
Kinematic Viscosity @ 40°C / 104°F	ASTM D 445/ ISO 3104	mm ² / s	151	222	317	465	673	956	1487
Kinematic Viscosity @ 100°C / 212°F	ASTM D 445/ ISO 3104	mm ² / s	14,7	18.9	23.6	29.9	35.9	42.7	54.7
Viscosity Index	ASTM D2270/ ISO 2909	-	97	96	95	95	94	86	80
Flash Point	ASTM D92/ ISO 2592	°C/°F	250/ 482	250/ 482	254/ 489.2	256/ 492.8	260/ 500	260/ 500	260/ 500
Pour Point	ASTM D97/ ISO 3016	°C/°F	-27/ -16.6	-24/ -11.2	-21/ -5.8	-21/ -5.8	-18/ -0.4	-18/ -0.4	-15/ 5
Water Separation @ 82°C / 180°F (40/37/3)	ASTM D1401/ ISO 6614	min	< 30	< 30	< 30	-	-	-	-
Rust Test (Method A, 24 hrs)	ASTM D665A/ ISO 7120	-	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Copper Corrosion (Corrosion Degree, 100 A3)	ASTM D130/ ISO 2160	-	1	1	1	1	1	1	1
Four Ball Wear Test (1 h, 40 kg, 1800 min-1, 75°C) Wear Scar Diameter	ASTM D2266	mm	0.4	0.4	0.4	0.4	0.4	0.4	0.4
FZG Test (A / 8.3 / 90) Scoring Load Stage	ISO 14635-1	FLS	>12	>12	>12	>12	>12	>12	>12
FZG Micropitting Test, Micropitting Load Carrying Capacity: High	FVA No. 54	-	10	10	10	10	10	10	10
Foaming Properties, Sequence I	ASTM D892/ ISO 6247	ml	0	0	0	0	0	0	0
Foaming Properties, Sequence II	ASTM D892/ ISO 6247	ml	< 50 / 0	< 50 / 0	< 50 / 0	< 50 / 0	< 50 / 0	< 50 / 0	< 50 / 0
Foaming Properties, Sequence III	ASTM D892/ ISO 6247	ml	0	0	0	0	0	0	0

Subject to usual manufacturing tolerances.

Additional Information

- Optigear 1100 gear oils are compatible with other petroleum gear oils. This means that traces of previous oil remaining in the gear case after draining will not pose any problems.
- However, the beneficial effects of the TGOA additives are reduced when Optigear 1100 gear oils are mixed with other gear oils.
- A thorough cleaning of the gearbox is highly recommended to achieve the maximum benefits.

This product was previously known as Tribol 1100 Range. The name changed in 2015.

Optigear™ 1100 Range

08 Jul 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

10 Junction Avenue , Parktown , Johannesburg , 2193 , South Africa
+27 11 488 5111, 0860 222 166 (SA), 0800 111 551 (SA)
www.castrol.co.za